

TEST REPORT

REPORT NUMBER :

TURA160016620

APPLICANT NAME

Sanem Matbaacılık A.Ş.

ADDRESS

Başkent Org.San.Böl. 19 .CaddeNo:85 Maliköy Ankara / TÜRKİYE

FAX: 0312 640 12 32

Attention : Abdurrahman Baştaş (abdurrahman@sanem.com.tr)

SAMPLE DESCRIPTION :

White plastic cover

BUYER :

TÜKİD

DATE IN :

02 February, 2016 (08:41)


DATE OUT :

08 February, 2016

PHOTO OF PRODUCT
TESTED :



Uğur Yılmaz
Coordinator



Neslihan Sözer
Chemical Laboratory Manager

Intertek Test Hizmetleri A.Ş.

Merkez Mahallesi Sanayi Cad. No: 23 Altındağ Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax : +90.212. 452 80 55

e-mail : intertekcg.turkiye@intertek.com

www.intertek-turkey.com



160016620

Code	Test Method	Result	Requirements
------	-------------	--------	--------------

Part No	Tested Sample
1	White plastic cover

Code	Test Method	Result	Requirements
------	-------------	--------	--------------

RESULTS :

Analysis Parameter	Reference Analysis Method	PASS	FAIL	Norm Limit	Standard for Norm Limit	Tested Sample
Allergenic Disperse Dyestuff	IHTM AL.2.090 & AL.2.178 refer to DIN 54231:2005	P	-	50 ppm	2002/371/EC	Part 1
Carcinogenic Disperse Dyestuff	IHTM AL.2.091 refer to DIN 54231:2005 By High Performance Liquid Chromatography & Mass Spectroscopy (LC-MS-MS) & HPLC-DAD Analysis	P	-	Not Detected	2002/371/EC	Part1
Azo Dyes	EN 14362-1 : 2012 for Textile Material	P	-	30 ppm	1907-2006-EC	Part 1
Phthalate	EN 14372 by GC MS	P	-	DBP/DEHP/BBP : 1000 ppm DINP/DNOP/ DIDP : 1000 ppm,	EEC Directive 2005/84/EC on 14 December 2005	Part 1
PAH	AfPS GS 2014:01	P	-	See PAH Test	2005/69/EC	Part 1
Toxic Element Analysis	BS EN 71-3:1995	P	-	Sb: 60 ppm As: 25 ppm Ba: 1000 ppm Cd: 75 ppm Cr: 60 ppm Pb: 90 ppm Hg: 60 ppm Se: 500 ppm	EN 71-3	Part 1

P = MEETS BUYER' S REQUIREMENT (GEÇTİ) / F = DOES NOT MEET BUYER' S REQUIREMENT (KALDI) / NR = NO REQUIREMENT (SINIR DEĞER BELİRTİLMEDİ) / SC=STILL CONTINUES (TEST İŞLEMİ DEVAM EDİYOR) / X=NOT PERFORMED (TEST EDİLMEDİ) / I = INCONCLUSIVE

"This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>."

"The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and TÜRKAK accreditation requirements. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered. When uncertainty is taken into account, the result may be borderline. Borderline results need to be re-tested to determine their disposition up to customer's decision. Opinions and interpretations expressed herein are outside the scope of TÜRKAK accreditation. Tests marked (*) in this test report are not included in the TÜRKAK accreditation schedule for this laboratory."

Code	Test Method	Result	Requirements
------	-------------	--------	--------------

Allergenic Disperse Dyestuff

IHTM AL.2.090:2010 & AL.2.178:2009 refer to DIN 54231:2005 By High Performance Liquid Chromatography & Mass Spectroscopy (LC-MS-MS) & HPLC – DAD Analysis :

<u>C.I. Generic Name</u>	<u>Part 1</u>
C.I. Disperse Blue 1:	ND
C.I. Disperse Blue 3:	ND
C.I. Disperse Blue 7:	ND
C.I. Disperse Blue 26:	ND
C.I. Disperse Blue 35:	ND
C.I. Disperse Blue 102:	ND
C.I. Disperse Blue 106:	ND
C.I. Disperse Blue 124:	ND
C.I. Disperse Brown 1:	ND
C.I. Disperse Orange 1:	ND
C.I. Disperse Orange 3:	ND
C.I. Disperse Orange 37/76:	ND
C.I. Disperse Orange 149:	ND
C.I. Disperse Red 1:	ND
C.I. Disperse Red 11:	ND
C.I. Disperse Red 17:	ND
C.I. Disperse Yellow 1:	ND
C.I. Disperse Yellow 3:	ND
C.I. Disperse Yellow 9:	ND
C.I. Disperse Yellow 23:	ND
C.I. Disperse Yellow 39:	ND
C.I. Disperse Yellow 49:	ND

ppm (part per million)	=mg / kg
Detection Limit	=3 ppm
<	=Less Than
ND	=Not Detected (Tespit Edilmedi)
Requirement	=50 ppm

(Total uncertainty=± 2 %)

Code	Test Method	Result	Requirements
------	-------------	--------	--------------

Carcinogenous Dyestuff

IHTM AL.2.091:2010 refer to DIN 54231:2005 By High Performance Liquid Chromatography (LC-MS-MS) & HPLC-DAD Analysis :

<u>COMPOUND</u>	<u>Part 1</u>
ACID RED 26	ND
BASIC RED 9	ND
BASIC VIOLET 14	ND
DIRECT BLACK 38	ND
DIRECT BLUE 6	ND
DIRECT RED 28	ND
DISPERSE BLUE 1	ND
DISPERSE ORANGE 11	ND
DISPERSE YELLOW 3	ND

ppm (part per million)	=mg / kg
Detection Limit	=0.5 mg/L
<	=Less Than
ND	=Not Detected
Requirement	=Not Detected

(Total uncertainty=± 3%)

Code	Test Method	Result	Requirements
------	-------------	--------	--------------

Detection Of Amines Derived From Azocolourants and Azodyes

By Gas Chromatographic – Mass Spectrometric (GC-MS) And High Performance Liquid Chromatographic (HPLC) Analysis.
Test Method : EN 14362-1 : 2012 for Textile Material

Part: 1

1- White plastic part (with extraction)

<30 ppm

INTERPRETATION OF AZO-DYES TEST RESULTS:

<u>FORBIDDEN AMINE</u>	<u>CAS NO</u>	<u>1</u>
4-AMINOBIHENYL	92-67-1	N
BENZIDINE	92-87-5	N
CHLORO-O-4-CHLOR-O-TOLUIDINE	95-69-2	N
2-NAPHTHYLAMINE	91-59-8	N
*O-AMINOAZOTOLUENE	97-56-3	N
*2-AMINO-4-NITROTOLUENE	99-55-8	N
P-CHLOROANILINE	106-47-8	N
2,4-DIAMINOANISOLE	615-05-4	N
4,4'-DIAMINOBIHENYLMETHANE	101-77-9	N
3,3'-DICHLOBENZIDINE	91-94-1	N
3,3'-DIMETHOXYBENZIDINE	119-90-4	N
3,3'-DIMETHYLBENZIDINE	119-93-7	N
3,3'-DIMETHYL-4,4' DIAMINOBIHENYLMETHANE	838-88-0	N
P-CRESIDINE	120-71-8	N
4,4'-METHYLENE-BIS-(2 CHLOROANILINE)	101-14-4	N
4,4'-OXYDIANILINE	101-80-4	N
4,4'-THIODIANILINE	139-65-1	N
O-TOLUIDINE	95-53-4	N
2,4-TOLUYLENDIAMINE	95-80-7	N
2,4,5-TRIMETHYLANILINE	137-17-7	N
O-ANISIDINE	90-04-0	N
**P-AMINOAZOBENZENE	60-09-3	N

Note:

- 1)The amines o-amino-azotoluene and 2-amino-4-nitrotoluene are detected by its splitted product o-toluidine and 2,4- toluylenediamine.
- 2)Azo colorants that are able to form 4-aminoazobenzene, generate under the condition of this method aniline and 1,4- phenylenediamine . The presence of these colorants can not be reliably ascertained without additional information, e.g. chemical structure of the colorant used.
- 3)According to EN 14362-1:2012, separate test is suggested to ascertain the compliance for result of mixed test in the range between 5 ppm and 30 ppm.
- 4)Azocolourants Content Requirement In Annex XVII Item 43 Of The REACH Regulation (EC) NO. 1907/2006 & Amendment No. 552/2009 and 126/2013 (Formerly Known As Directive 2002/61/EC

ppm : part per million (mg/kg)

Detection Limit: 5 ppm

< = Less Than

Total Uncertainty = ± 9%

N:Not detected

Code	Test Method	Result	Requirements
------	-------------	--------	--------------

TOTAL PHTHALATE CONTENT

EN 14372 : 2004 Method By Gas Chromatographic-Mass Spectrometric (GC-MS) Analysis :

	<u>Part 1</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND

REMARK =The Above Limit Was Quoted According To The EEC Directive 2005/84/EC On 14 December 2005.
ND =Not Detected (Tespit Edilmedi)
ppm (part per million) =mg / kg
Detection Limit =DIDP, DINP: 100 ppm, Other Phthalates: 10 ppm
< =Less Than
* =EXCEEDED LIMIT
LIMIT (MAX.) =DBP,DEHP,BBP < 1000 ppm ; DINP, DNOP, DIDP < 1000 ppm

(Total Uncertainty=±5 %)

Code	Test Method	Result	Requirements
Polycyclic Aromatic Hydrocarbons (PAHs) Analysis			
INTERTEK IHTM AL.2.032 : 2012 based on AfPS GS 2014:01			
		RESULT	REQUIREMENT
			Category 2
			Materials not covered by category 1, with foreseeable skin contact for longer than 30 seconds (long-term skin contact) or repeated short-term skin contact ¹) (ppm)
		Part 1	Other products in the scope of ProdSG
1	Benzo (a) pyrene	ND	<0.5
2	Benzo (e) pyrene	ND	<0.5
3	Benzo (a) anthracene	ND	<0.5
4	Benzo (b) fluoranthene	ND	<0.5
5	Benzo (j) fluoranthene	ND	<0.5
6	Benzo (k) fluoranthene	ND	<0.5
7	Chrysene	ND	<0.5
8	Dibenzo (a,h) anthracene	ND	<0.5
9	Benzo (g,h,i) perylene	ND	<0.5
10	Indeno (1,2,3-cd) pyrene	ND	<0.5
11	Acenaphthylene	ND	<10
12	Acenaphthene	ND	
13	Fluorene	ND	
14	Phenanthrene	ND	
15	Pyrene	ND	
16	Anthracene	ND	
17	Fluoranthene	ND	
18	Naphthalene	ND	
	Sum of 18 PAH	ND	<10
	ppm (part per million) =mg / kg		
	Detection Limit = 0.2 ppm		
	ND = Not Detected (Tespit Edilmedi)		

Estimated Total Uncertainty= ±3%

Code	Test Method	Result	Requirements
------	-------------	--------	--------------

Toxic Elements Analysis

BS EN 71-3:1995

Acid extraction method was used and toxic elements content were determined by Inductively Coupled Plasma-ICP_OES.

<u>Part 1</u>		
Antimony	(Sb)	ND
Arsenic	(As)	ND
Barium	(Ba)	ND
Cadmium	(Cd)	ND
Chromium	(Cr)	ND
Lead	(Pb)	ND
Mercury	(Hg)	ND
Selenium	(Se)	ND

		<u>Detection Limit</u>	<u>Requirement (ppm)</u>
Antimony	(Sb)	2 ppm	<60
Arsenic	(As)	2 ppm	<25
Barium	(Ba)	2 ppm	<1000
Cadmium	(Cd)	2 ppm	<75
Chromium	(Cr)	5 ppm	<60
Lead	(Pb)	5 ppm	<90
Mercury	(Hg)	2 ppm	<60
Selenium	(Se)	2 ppm	<500

(Total uncertainty=Results quoted have been corrected for uncertainty)

ppm (Part per million)

<

ND

=mg / kg

=Less Than

=Not Detected

END OF TEST REPORT

Intertek Test Hizmetleri A.S.

Merkez Mahallesi Sanayi Cad. No. 23 Altındağ Plaza Yenibosna 34197 - ISTANBUL / TURKEY

Phone : +90.212. 496 46 46 Fax : +90.212. 452 80 55

e-mail : intertekcg.turkiye@intertek.comwww.intertek-turkey.com